

## Nelco® N9000

### PTFE Laminates

The N9000 PTFE laminate system is designed for critical microwave components, antennas, power amplifiers and subassemblies. Superior mechanical and electrical performance make the N9000 PTFE laminate system the material of choice for your lowest loss, high frequency applications.

### Key Features

#### Complete spectrum of controlled dielectric constants

- Dk of 2.08 through Dk of 4.50
- The first reinforced PTFE laminate with a dielectric constant less than 2.17 for very low loss antenna designs
- Available in sheets up to 80 inches long (2.03 meters) by 48 inches wide (1.22 meters)

#### Enhanced N9000 IM materials available

- Enables reduced passive intermodulation in antenna and high power designs - up to up to 25% better than other PTFE laminates available
- Offers two-tone passive intermodulation performance of less than -155 dBc which is typically 8-20 Db lower than other PTFE materials available.

#### Consistent Quality

- Statistic Process Control "SPC" methods provide consistent dielectric values from sheet to sheet and lot to lot
- Nelco facilities are ISO 9001:2000 quality certified and comply to ISO 14001:2004 environmental regulations
- Meets UL 94V-0 specifications
- All Nelco materials are RoHS compliant.

#### Optimized N9000 PTFE processing

- Foil adhesion is 50-100% greater than competitive glass reinforced PTFE laminates and 200-300% greater than other ceramic loaded hydrocarbon laminates.
- Superior solvent absorption resistance compared to ceramic-loaded PTFE.
- Reduced dielectric constant changes due to solvent absorption and no additional baking cycles are needed during processing



### Applications

- Cellular Base Station Antennas
- Wireless Communications
- Power Amplifiers
- Dual Band Hi Power Passive Circuits
- Automotive Applications
- Digital/Microwave Hybrid Multilayer PCB Assemblies
- Millimeter Wave Components
- Telecommunications

### Global Availability

Nelco Products, Inc. (California) - Americas  
+1.714.879.4293  
Neltec, Inc. (Arizona) - Americas  
+1.480.967.5600  
Nelco Products Pte. Ltd. - Asia Pacific  
+65.6861.7117  
Neltec, S.A. - Europe  
+33.562.98.52.90  
www.parkelectro.com  
info@parkelectro.com

**Park's UL file number: E36295**



## Nelco® N9000 Series - Typical Engineering Values

Typical Parameter	9270	9294	9300	9320	9294	9300	9320	9338	9348	9350	9410	9450
Dielectric Constant at 10 GHz (Dk)	2.70±.04	2.94±.04	3.00±.04	3.20±.04	NH SERIES							
Dissipation Factor at 10 GHz (Df)	0.0020	0.0022	0.0023	0.0024	NH SERIES							
PIM Formulation Availability	Yes											
Passive Intermodulation Performance	-155 dBc											
Dielectric Breakdown	50kV											
Volume Resistivity	10 <sup>9</sup> M / cm											
Surface Resistivity	10 <sup>7</sup> M											
Arc Resistance	180 sec.											
Flexural Strength Lengthwise	82.7 MPa											
Flexural Strength Crosswise	68.9 MPa											
Copper Peel Strength - 18, 35, 70 µm (1/2 oz, 1 oz, and 2 oz copper)	2.33 kN / m											
After Thermal Shock (30 sec. at 260°C)	2.31 kN / m											
Moisture Absorption	0.02%											
Specific Gravity	2.23 g / cm <sup>3</sup>											
Thermal Conductivity	0.272 W / m / K											
Coefficient of Thermal Expansion (CTE)	2.31 kN / m											
X	0.08%											
Y	2.459 g / cm <sup>3</sup>											
Z	0.230 W / m / K											
Flammability	9 ppm / °C											
	12 ppm / °C											
	71 ppm / °C											
	V-0											

For non-standard dielectric constants or additional copper foil options, please contact the factory or your local Nelco representative.

### Ordering Information

Please specify the product and / or Dk, material thickness, copper thickness, copper type, and panel size. Request Passive Intermodulation Formulation when necessary for antenna applications.

Example: 9220, .010" thick, 1 oz two sides, ED copper, 12"x18" or Dk=2.20, .010" thick, 1 oz copper two sides, ED copper, 12"x18". For Passive Intermodulation Formulation material, add the IM suffix, i.e.: 9220IM.

# Park Advanced Circuitry Materials

## Nelco® RF and Microwave Materials

**N4350-13 RF** Controlled Dk/Df Modified Epoxy  
Dk 3.50 / Df 0.0065 at 10 GHz

**NH9000**

Woven, Glass / Ceramic Loaded PTFE  
Dk 2.94 - 4.50 / Df 0.0022 - 0.0030

**N4380-13 RF** Controlled Dk/Df Modified Epoxy  
Dk 3.80 / Df 0.0070 at 10 GHz

**NX9000**

Woven Glass Reinforced PTFE  
Dk 2.40 - 3.20 / Df 0.0016 - 0.0024

**N9000-13 RF** PTFE and Epoxy Composite  
Dk 3.00 / Df 0.0040 at 10 GHz  
Dk 3.20 / Df 0.0045 at 10 GHz  
Dk 3.38 / Df 0.0046 at 10 GHz  
Dk 3.50 / Df 0.0055 at 10 GHz

**NY9000**

Woven Glass Reinforced PTFE  
Dk 2.08 - 2.33 / Df 0.0006 - 0.0011

Above values at 10 GHz

### Nelco® N9000 Material - Standard Laminate Thicknesses

Series	Product	0.005	0.010	0.015	0.020	0.030	0.031	0.045	0.060	0.062	0.125
		0.127	0.254	0.381	0.508	0.762	0.787	1.143	1.524	1.575	3.175
NY	9208					X			X		X
NY	9217	X	X	X	X	X	X	X	X	X	X
NY	9220	X	X	X	X	X	X	X	X	X	X
NY	9233	X	X	X	X	X	X	X	X	X	X
NX	9240	X	X	X	X	X	X	X	X	X	X
NX	9245	X	X	X	X	X	X	X	X	X	X
NX	9250	X	X	X	X	X	X	X	X	X	X
NX	9255	X	X	X	X	X	X	X	X	X	X
NX	9260	X	X	X	X	X	X	X	X	X	X
NH	9294	X	X	X							
NX	9294				X	X	X	X	X	X	X
NH	9300	X	X	X							
NX	9300				X	X	X	X	X	X	X
NH	9320	X	X	X	X						
NX	9320					X	X	X	X	X	X
NH	9338	X	X	X	X	X	X	X	X	X	X
NH	9348	X	X	X	X	X	X	X	X	X	X
NH	9350		X	X	X	X	X	X	X	X	X

inches  
mm

#### Constructions

NY: PTFE / woven-glass composite. Low glass:PTFE ratio for lowest loss applications.

NX: PTFE / woven-glass composite. Medium glass:PTFE ratio for increased mechanical strength.

NH: PTFE / woven-glass / ceramic composite. Medium glass:PTFE ratio with ceramic added for thermal stability and Dk uniformity at higher Dks.

Park Electrochemical Corp. is a global advanced materials company which develops and manufactures high-technology digital and RF/microwave printed circuit materials and advanced composite materials, parts and assemblies. The company operates under the Nelco®, Nelcote® and Nova™ names.

All test data provided are typical values and not intended to be specification values. For review of critical specification tolerances, please contact a Nelco representative directly. Nelco reserves the right to change these typical values as a natural process of refining our testing equipment and techniques.

Aeroglide™, CoreFix®, Easycure™, EF®, EP™, LD®, Mercurywave™, Nelco®, Nelcote®, Nova™, PeelCote™, RTFoil® and SI® are trademarks of Park Electrochemical Corp.

\*CAF resistance has been established to greater than 500 hours using a specific OEM coupon design and test procedure. For details on this or other CAF tests, please visit [www.parkelectro.com](http://www.parkelectro.com).

Nelco reserves the right to make changes without further notice to any products herein to improve reliability, function or design. Nelco does not assume any liability arising out of the application or use of any product described herein; neither does it convey any license under its patent rights nor the rights of others. This disclaimer of warranty is in lieu of all warranties whether expressed, implied or statutory, including implied warranties of merchantability or fitness for a particular purpose.

